



EXPERIENCE TO PERFORM

TECHNICAL DATA SHEET

MOTORSIL D

HIGH PERFORMANCE SILICON GASKET

- PRODUCT DESCRIPTION

Product for seal gasket forms any kind of gasket thickness. Allows to form dynamic and elastic connections. Fills micro-spaces which were caused by a non perfect planarity, substitutes all types of preformed gaskets.

Autolevelling, hardens without any loss of volume.

At ambient temperature reticulates by humidity process.

- APPLIANCE FIELD

To apply in substitution or as adjuvant for any type of preformed gasket. Adapted also for motors which have a catalytic converter; The products has a low volatility without risk of compromising the functionality of the lambda feeler.

Product is easy to remove.

- TECHNICAL CHARACTERISTICS

(before reticulation)

• Apparence	Autolevelling paste
• Colour	Red
• Odour	characteristic
• Reticulation	acetic
• Density	1,120 g/ml
• Viscosity	250.000 cPs
• Volatillity %	3 % ca.

(after reticulation)

• Hardness shore A	50
• Elongation break	200 %
• Resistance to tensile stress	4,5 MPa
• Module of elasticity (100% di allungamento)	1,8 MPa
• DCR (remaining deformation to compression)	35 %

(operation start)

• Time for rind forming	10 minutes
• Time of reticulation	4,5 mm/24 h
• Temperature exercise	
- continueo	-70° ÷ 250°C
- peacks	Up to 300°C

After reticulation, the product resists to water, fuels, mineral and synthetic oils, radiator liquids.

- INSTRUCTIONS FOR USE

Apply on clean and degreased surfaces. After ca. 20 minutes assemble the single parts (forming of rind). Possibility to accelerate the reticulation with warmth.

- STORAGE

Entirely packed, conserved at ambient temperature and safe from direct sunlight: 2 years

- ATTENTION

During the hardening process, developing of acetic acid vapour traces.

Avoid long contact of the product with skin and eyes; in case of contact with eyes wash abundantly with water.

- PACKAGING

Alluminum tube
Content 60 g.
Cod. 0096

- NOTICE

For product security information consult the material safety

R&D 05.04.2011 REV.0

The data contained herein are the result of technological research by our laboratories and are given for informative purposes only. We exclude any liability deriving from the incorrect choice or application of the product and from the lack of the necessary precautions, which should be carefully checked by the user. For information, please contact our Technical Dept. on no. +39 02924361

AREXONS S.p.A. A SOCIO UNICO
Via Antica di Cassano, 23
20063Cernusco sul Naviglio (MI) Italy
Capitale Sociale: € 15.000.000,00 I.V.
Registro delle Imprese di Milano n. 09728360968
Codice Fiscale e Partita IVA 09728360968
Direzione e coordinamento ex art. 2497 c.c. PLI (Netherlands) B.V.
Centralino 02 92436.1
Fax 02 92436.306
www.arexons.com

A wholly-owned subsidiary of PETRONAS

Sistemi di gestione di qualità della società Arexons S.p.A.
certificati ISO 9001 da LRQA.

Sistemi di gestione di ambiente e sicurezza della società Arexons S.p.A.
certificati ISO 14001 e OHSAS 18001 da Bureau Veritas.

